



PSB Singapore

**Note:** This report is issued subject to TÜV SÜD PSB's "Terms and Conditions Governing Technical Services".  
The terms and conditions governing the issue of this report are set out as attached within this report.

Choose certainty.  
Add value.

**SUBJECT:**

Large scale surface spread of flame test on "SIU - BF Panel" Sound Innovation Universal Acoustic Wall and Ceiling Panel submitted by BA Contracts Pte Ltd on 15 Jun 2010.

**TESTED FOR:**

BA Contracts Pte Ltd  
10 Admiralty Street  
#06-30  
North Link Building  
Singapore 757695

Attn: Mr John Goh

**DATE OF TEST:**

21 Jul 2010

**PURPOSE OF TEST:**

To determine the tendency of the surface of a material or a combination of materials to support the spread of flame across its surface and to classify the surface according to the test given in British Standard 476 : Part 7 : 1997.

The test was conducted at TÜV SÜD PSB's fire test laboratory located at No. 10 Tuas Avenue 10, Singapore 639134.



Laboratory:  
TÜV SÜD PSB Pte. Ltd.  
No.1 Science Park Drive  
Singapore 118221

Phone : +65-6885 1333  
Fax : +65-6776 8670  
E-mail: testing@tuv-sud-psb.sg  
www.tuv-sud-psb.sg  
Co. Reg : 199002667R

Regional Head Office:  
TÜV SÜD Asia Pacific Pte. Ltd.  
3 Science Park Drive, #04-01/05  
The Franklin, Singapore 118223  
TUV®



LA-2007-0380-A  
LA-2007-0380-A-1  
LA-2007-0381-F  
LA-2007-0382-B  
LA-2007-0383-G  
LA-2007-0384-G  
LA-2007-0385-E  
LA-2007-0386-C

The results reported herein have been performed in accordance with the laboratory's terms of accreditation under the Singapore Accreditation Council - Singapore Laboratory Accreditation Scheme. Tests/Calibrations marked "Not SAC-SINGLAS Accredited" in this Report are not included in the SAC-SINGLAS Accreditation Schedule for our laboratory.

## DESCRIPTION OF SPECIMENS:

Nine pieces of specimen, said to be "SIU - BF Panel" (4mm to 20mm thick x 1050kg/m<sup>3</sup>) Sound Innovation Universal Acoustic Wall and Ceiling Panel comprising of approximately 0.8mm thick High Pressure Laminate / Wood and Glass Fiber Magnesium Cement Board / approximately 1.2mm thick Wood Veneer and High Pressure Laminate, each of nominal size of 885mm x 270mm were submitted. The brand of the fire retardant adhesive used was said to be "Internet". The overall thickness of the specimen was found to be approximately 14.1mm.

## TEST PROCEDURE:

Prior to test, the specimens were prepared and conditioned in accordance with paragraphs 5.3 to 5.6 of the standard and secured to a specimen holder as described in paragraph 6.3.

Six specimens, backed with calcium silicate board, were tested with the high pressure laminated face exposed to the specified thermal radiation from the apparatus described in paragraph 6.1 of the standard. The intensity of the radiated heat incident on the specimen varies with distance from the hotter end, so that when the specified calibration panel is mounted in the place to be occupied by the specimen, the irradiance of the radiometer is as given in Table 1. The test was terminated when the flame front reached the 825mm reference line, or after 10 minutes has elapsed, whichever is the shorter.

**Table 1 : Irradiance Along Horizontal Reference Line on the Calibration Board**

Distance along reference line from inside edge of specimen holder  mm	Irradiance kW/m <sup>2</sup>		
	specified	min.	max.
75	32.5	32.0	33.0
225	21.0	20.5	21.5
375	14.5	14.0	15.0
525	10.0	9.5	10.5
675	7.0	6.5	7.5
825	5.0	4.5	5.5





## RESULTS OF TEST:

Specimen No.	1	2	3	4	5	6
Spread of flame at first 1½ minutes (mm)	0	0-75	75-165	0-75	0-75	0-75
Distance (mm)	Time of spread of flame to indicated distance (minutes • seconds)					
Start of flaming	nil	0.01	0.52	0.39	0.42	0.59
75	-	-	1.08	-	-	-
165	-	-	-	-	-	-
190						
215						
240						
265						
290						
375						
455						
500						
525						
600						
675						
710						
750						
785						
825						
865						
Time of maximum spread of flame (minutes • seconds)	0	1.37	2.58	1.50	1.47	1.33
Distance of maximum spread of flame (mm)	-	0-75	75-165	0-75	0-75	0-75
Comments	None					



**Classification of Surface Spread of Flame**

Classification	Spread of flame at 1.5 min.		Final spread of flame	
	Limit (mm)	Limit for one specimen in sample (mm)	Limit (mm)	Limit for one specimen in sample (mm)
Class 1	165	165 + 25	165	165 + 25
Class 2	215	215 + 25	455	455 + 45
Class 3	265	265 + 25	710	710 + 75
Class 4	Exceeding the limits for class 3			

**CONCLUSION:**

In accordance with the class definitions specified in the Standard, the test results show that the sample tested has a Class One Surface Spread of Flame.

**REMARKS:**

1. The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.
2. The test was witnessed by Mr John Goh of BA Contracts Pte Ltd.

  
\_\_\_\_\_  
Ong Kian Huat  
Associate Engineer

  
\_\_\_\_\_  
Chan Lung Toa  
Product Manager  
(Fire Safety & Security Products)  
Mechanical Centre



**This Report is issued under the following conditions:**

1. Results of the testing/calibration in the form of a report will be issued immediately after the service has been completed or terminated.
2. Unless otherwise requested, this report shall contain only technical results carried out by TÜV SÜD PSB. Analysis and interpretation of the results and professional opinion and recommendations expressed thereupon, if required, shall be clearly indicated and additional fee paid for, by the Client.
3. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
4. The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
5. Additional copies of the report are available to the Client at an additional fee. No third party can obtain a copy of this report through TÜV SÜD PSB, unless the Client has authorised TÜV SÜD PSB in writing to do so.
6. TÜV SÜD PSB may at its sole discretion add to or amend the conditions of the report at the time of issue of the report and such report and such additions or amendments shall be binding on the Client.
7. All copyright in the report shall remain with TÜV SÜD PSB and the Client shall, upon payment of TÜV SÜD PSB's fees for the carrying out of the tests/calibrations, be granted a license to use or publish the report to the third parties subject to the terms and conditions herein, provided always that TÜV SÜD PSB may at its absolute discretion be entitled to impose such conditions on the license as it sees fit.
8. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
9. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
10. Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, No.1 Science Park Drive Singapore 118221.

March 2010